

Granulát	mm	2,800	2,360	2,000	1,700	1,400	1,180	1,000	0,850	0,710	0,650	0,500	0,425	0,355	0,300	0,180	0,125							
SAE	7	8	10	12	14	16	18	20	25	30	35	40	45	50	80	120								
S780	AP			MIN 8 5 %	MIN 9 7 %																			
S660		AP			MIN 8 5 %	MIN 9 7 %																		
S550			AP			MIN 8 5 %	MIN 9 7 %																	
S460				AP	MAX 5 %		MIN 8 5 %	MIN 9 6 %																
S390					AP	MAX 5 %		MIN 8 5 %	MIN 9 6 %															
S330							AP	MAX 5 %		MIN 8 5 %	MIN 9 6 %													
S280									AP	MAX 5 %		MIN 8 5 %	MIN 9 6 %											
S230											AP	MAX 10 %		MIN 8 5 %	MIN 9 7 %									
S170													AP	MAX 10 %		MIN 8 5 %	MIN 9 7 %							
S110															AP	MAX 10 %		MIN 8 0 %	MIN 9 0 %					
S70																				AP	MAX 10 %		MIN 8 0 %	MIN 9 0 %