

Chemical composition	Summary
ZrO ₂	60 - 70 %
SiO ₂	28 - 33 %
Al ₂ O ₃	< 10 %